



Specialty Ano-EE

Hardcoat Additive

1. Description

Specialty Ano-EE is a unique liquid additive for higher temperature Type III anodizing.

- Hardcoat at 60°F
- Requires less refrigeration, thus savings on chilling energy cost.
- Complies with Military Specifications for Type III hardcoat anodizing.
- Improves the uniformity of film thickness throughout the entire anodizing tank.
- Virtually eliminates burning.
- Will not yellow or stain the coating.
- Parts will be clearer in appearance.
- The dye-ability of hardcoat films is improved.
- RoHS compliant
- REACH compliant

2. Application instructions

Use of Ano-EE to produce 2.0 mils, "Hardcoat" anodic oxide coatings.

Ano-EE concentration: 3%-4% by volume

Sulfuric acid concentration: 170-190 g/l

Dissolved aluminum concentration: 5-15 g/l

Temperature: 45-60°F

Current: 24-48 ASF

3. Titration procedure

Reagents: 0.1N ferrous ammonium sulfate (FAS)
50% sulfuric acid
Ferriin indicator
0.1N ceric sulfate solution

Procedure: Step 1 of 2 (standardization)

1. Pipette 25-mls of the 0.1N ferrous ammonium sulfate into a 400 ml beaker.
2. Add 100-mls of distilled water.
3. Add 25-mls of 50% sulfuric acid solution.
4. Add 4 drops of ferriin indicator.
5. Titrate with 0.1N ceric sulfate solution until the orange color disappears.

Calculation: $\frac{\text{mls of ceric sulfate}}{25} = "F"$

Note:

FAS solution should be discarded if the amount of 0.1N ceric sulfate solution required for this titration is less than 15 milliliters.

Procedure: Step 2 of 2 (anodize bath analysis)

1. Pipette 10-mls of the anodizing solution into a 1-liter volumetric flask.
2. Add deionized water to the 500-ml mark and mix well.
3. Pipette 25-mls of the dilute solution into a 400-ml beaker.
4. Add 25-mls of 50% sulfuric acid.
5. Using a pipette, accurately add 25-mls of 0.1 ceric sulfate solution.
6. Add 2-3 pieces of glass bead and boil 10-15 minutes.
7. Cool and add distilled water to the 200-ml mark.
8. Add 4 drops of ferroin indicator and titrate to an orange end point with 0.1N FAS. Record mls of FAS as "A".

Calculation: $\frac{25 - (A \times F)}{2.67} = \% \text{ by volume Specialty Ano-EE}$

4. **Storage**

Store in original container in a dry location.

5. **Packaging**

1 gallon
5 gallons
55 gallons

6. **Product safety**

We recommend that the company/operator read and review the **Safety Data Sheet** for the appropriate health and safety warnings before use.

U.S. Specialty Color Corporation® recommendations, notices or instructions as to handling, use, storage of any product, including its use alone or in combination with other products, or as to any apparatus or process for the use of any product, are based upon information believed to be reliable, but U.S. Specialty Color Corporation® shall have no liability with respect to any recommendations or instructions. U.S. Specialty Color Corporation® sole and exclusive warranty is that its products comply with U.S. Specialty Color Corporation® published chemical and physical specifications. U.S. Specialty Color Corporation® makes no other warranties, other express or implied with respect to its recommendations, instructions, products, apparatus, and process or otherwise and specifically disclaims any implied warranties of merchantability, suitability, fitness for a particular or otherwise.